

<b>Product name</b>	:	<b>BENMAN PRIMER</b>			
<b>Colour</b>	:	<b>White</b>	<b>Grey</b>	<b>Red</b>	<b>Black</b>
<b>Reference number</b>	:	<b>28 552</b>	<b>28 553</b>	<b>28 554</b>	<b>43 573</b>

### Product description

High quality, fast drying primer to treat surfaces, treated or untreated, of wood, metal, aluminium, glass, stone, and various types of plastic.  
Suitable primer as pre treatment for re-spraying with all lacquer systems (alkyd resin, nitro cellulose, 1-K acrylic and 2-K acrylic lacquers).

### Product characteristics

Fast drying  
Excellent coverage and filling property  
Corrosion preventive  
Easy to sand, both wet and dry (from grain 400)  
Re-sprayable with all lacquer systems

### Physical and Chemical Characteristics

Contents	: 400 ml
Base	: Nitro-cellulose binder
Colour 400 ml	: White, Grey, Red
VOC-content	: Approximately 84% w/w
Solid content	: Approximately 16% w/w
Coverage	: 1,25 to 1,75 m <sup>2</sup>
Dust dry	: After 5 to 10 minutes
Tack free	: After 10 to 20 minutes
Hardened/Re-sprayable	: After 2 hours
Heat resistant	: up to 110°C



### Usage

**Before use, carefully read the directions on the packaging and act accordingly.**

#### Pre Treatment

The surface should be clean, dry and free of grease.  
Remove loose old lacquer and rust and sand the surface.

#### Treatment

The surface should be clean, dry and free of grease.  
The can should have room temperature. Best application temperature 15 to 25°C. Before use, shake the can for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimeters.

Apply the product in several thin layers. Before applying the next layer, again shake the can.  
After use, clean the valve (turn can upside down and press the nozzle for approximately 5 seconds).

**The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.**